Progress in EUV Collector Technology at SAGEM

Roland GEYL, Renaud MERCIER YTHIER, Xavier BOZEC, André RINCHET SAGEM SA - REOSC High Performance Optics

Avenue de la Tour Maury 91280 Saint Pierre du Perray - France contact: renaud.mercierythier@sagem.com

This poster presents SAGEM various line of R&D effort toward precision optics for EUV applications. Generic EUV optics background, and specific progress in designing and manufacturing of EUV mirrors and collectors are highlighted.

SAGEM Background in EUV Optics


SAGEM participates to the European EUV R&D effort

PREUVE project with Leti - Manufacture of the BEL 2000-2002 2002-2004

EXTATIC and EXTUMASK programS within EU MEDEA+ frame

2004-2006 More Moore program within EU ISTframe

Eagle Program (European consortium of manufacturers led by ASML) 2006-2007





•EUV optics example : The BEL Schwarzschilds

Design: FOV=100 μm, NA=0.32, Aspherized mirrors, Mag: 10x, large mirror diameter 220 mm

Optical performance:

< 0.15 nm RMS HSFR (per mirror)

< 0.20 nm RMS MSFR (per mirror)

< 1.8 nm RMS transmitted WFE (full system)

Collectors Design

Collectors for DPP and LPP source (Eagle studys)


Collection angle: up to 80°

Throughput up to 45 % of 2π sr


Good image quality thanks to mirrors aspherisation

Design compliant with foil trap for debris mitigation Uniform pupil fill compared to grazing incidence collectors

Easy cooling implementation on mirror's rear side



Collector for LPP source




Substrate Machining & cooling


Sagem has recently conducted extensive technological studies and breadboard activities on low cost EUV collector substrates

Substrate materials for EUV mirrors


Sagem has experience with the following substrates:

- -Glassy material (Zerodur, Fused Silica)
- Silicon or SiC
- -Metal materials





Thermal study with water cooling



Slim channel technology

Cooling and machining

EUV mirrors close to the source receives a large flux Efficient cooling has been studied by Sagem in the scope of Eagle

Small channels are machined very close to the optical face allowing an efficient cooling to ambiant temperature without degrading the optical performances

Ultra Smooth Polishing

Within Eagle, specific polishing development has been conducted on different substrates.

MSFR (period 2 µm - 1 mm) LSFR (period 1 mm - 250 mm) HSFR (period 10 nm - 2 µm) Name Value of the Control of the Con **Glassy Material** < 0.5 Å 0.8 Å RMS Asphere figured over Ø 350 mm over 1 - 100 mm⁻¹ down < 1 nm RMS Interferometry Bit 3 TFA Big Alon Mark Bit 3 TFA Big Alon A Bit 3000 A **Silicon Material** < 0.7 Å 4 Å RMS 200 mm EUV mirror **Metallic Substrate** Sec. 3.17 A.

Eq. 4.04 A.

Eq. 4.04 A.

En. 20.05 A.

En. < 2 Å 4 Å RMS

Wyko measurement AFM measurement Works have been made by Sagem on the ultra-smooth polishing of different materials in order to lower


INSTITUT

EUV coating

Sagem is actively preparing its capability to transfer EUV coating technology to its large coating facility for industrial production of large normal EUV collectors.

the cost of EUV mirrors. These good results are obtained on large asphere mirrors

- Development made with Paris Institute of Optics
- •200 mm diameter mirrors can be coated.
- Works on enlarged capabilities initiated.
- Technology: Magnetron sputtering or IBS
- •Design: stack of 40 Mo/Si bi-layers, stability reinforced with interdiffusion barriers
- •Gradient: required when incidence variation exceeds a few degrees •Metrology :
 - -Small angle X ray reflectivity
 - Diffuse X ray scattering
 - -AFM






Coating with gradient

X ray reflectivity vs i

Measured at Lure Synchroton

•In 2007 qualification of an EUV coating with interfdiffusions barriers have shown its stability after annealing, EUV exposure, thermal cycling and humidity exposure. Other designs under evaluation.



•In the scope of Eagle, good stability of this coating has been shown after annealing at 300 ℃

Conclusion

•Thanks to Eagle studies and recent contracts, big progress has been made by Sagem in the polishing, coating and cooling of ultra smooth mirrors for EUV sources.

•Complete solutions can now be proposed for EUV mirrors and collectors, in line with the stringent requirements required by the EUV field.

